

Type Test Report

based on Regulation (EU) No 305/2011



Notification No.: 1008

Test Report No.: 28240341 001 **Order No.:** 93356030 **Page 1 / 3**

Client: JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD.
No.1 Zhongtian Road, Hekou Town, Rudong County, 226463 Jiangsu Province, CHINA

Test item: Optical Fiber Cable

Manufacturer and manufacturing plant: JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD.
No.1 Zhongtian Road, Hekou Town, Rudong County, 226463 Jiangsu Province, CHINA

Identification: ZTT GYFJH-4F (ZTT 0521) *Serial No.:* -

Receipt No.: A000170070-003 *Date of receipt:* 2017.07.31.

Testing location: TÜV Rheinland InterCert Kft. Termék üzletág Villamos laboratórium
H-1132 Budapest, Váci út 48/A-B, Hungary

Test specification: EN 60332-1-2:2004 + A1:2015
EN 60332-1-1:2004 + A1:2015

Test Result: This type-test report performed by the given test specification contains
- the measuring data, results and statements according to the reference of the product-type by System in Annex V. of regulation 305/2011/EU. for



Harmonised standard: EN 50575:2014 + A1:2016
Classification standard: EN 13501-6:2014

Throughout this report a comma is used as the decimal separator

Abbreviations: ok / P = passed
fail / F = failed
n.a. / N/A = not applicable
data / D = publication of data

This test report relates to the a. m. test item. Without permission of the test center this test report is not permitted to be duplicated in extracts.

TÜV Rheinland InterCert Kft. – H-1132 Budapest, Váci út 48/A-B
tel.: +36/1/4611150; fax: +36/1/4611199; e-mail: tuv@hu.tuv.com – honlap: www.tuv.hu

EN 60332-1-2			
Clause	Requirement + Test	Result	Remark

ZTT GYFJH-4F 7.0mm (ZTT 0521)			
5	Procedure		
	Sample length (600 ± 25 mm).....:	615	P
	Approx. outer diameter (mm).....:	7,0	
	Flame application time (s).....:	60	P
6	Evaluation of test results		
	Not damaged area from lower edge of the top support (min. 50 mm).....:	395	P
	Damaged area from lower edge of the top support (max. 540 mm).....:	495	P
	Flame spread H (max. 425 mm).....:	100	P

Test Type:	Test for vertical flame propagation for a single insulated wire or cable 1 kW pre-mixed flame
Standard:	EN 50575:2014 + A1:2016, EN 13501-6:2014 EN 60332-1-2:2004 + A1:2015, EN 60332-1-1:2004 + A1:2015
Cable type:	ZTT GYFJH-4F 7.0mm (ZTT 0521)
Marking:	ZTT GYFJH-4F 7.0mm Optical Fiber Cable ZTT0521 2017/06/24 0052M
Manufacturer:	JIANGSU ZHONGTIAN TECHNOLOGY CO., LTD.
No. of samples:	1
Ambient temperature:	26,5 °C
Date of test:	2017.08.07.
Classification according to EN 13501-6:	E_{ca}

Photo documentation

Before test
After test
Measuring equipment list

Device	Manufacturer	Type	Identification No.	Next calibration
Measuring tape	Stabila	BM 30W	503509	2019.09.21.
Stop-watch	Helvetia	S001	502911	2017.10.25.
Digital caliper	Mitutoyo	CD-15B	0556014003	2018.01.03.
Digital temperature and humidity meter	Testo	testo 635	023302	2018.01.24.
1 kW pre-mixed burner	MEEI	-	01629026	2018.03.14

-END OF TEST REPORT-